



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B22D 21/04, 17/30, 17/08, 17/02		A1	(11) International Publication Number: WO 99/28065
			(43) International Publication Date: 10 June 1999 (10.06.99)
(21) International Application Number: PCT/AU98/00987		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 30 November 1998 (30.11.98)		<p>Published With international search report.</p>	
(30) Priority Data: PP 0604 28 November 1997 (28.11.97) AU			
(71) Applicant (for all designated States except US): COMMON-WEALTH SCIENTIFIC AND INDUSTRIAL RESEARCH ORGANISATION [AU/AU]; Limestone Avenue, Campbell, ACT 2612 (AU).			
(72) Inventors; and (75) Inventors/Applicants (for US only): MURRAY, Morris, Taylor [AU/AU]; 51 Teal Lane, Briar Hill, VIC 3088 (AU). COPE, Matthew, Alan [GB/AU]; 118 Jones Road, Somerville, VIC 3912 (AU).			
(74) Agent: CROSS, Robert, N.; Phillips Ormonde & Fitzpatrick, 367 Collins Street, Melbourne, VIC 3000 (AU).			

(54) Title: MAGNESIUM PRESSURE CASTING

(57) Abstract

The provision or use, for the pressure casting of magnesium alloy in a molten or thixotropic state with a pressure casting machine having a mould or die which defines a die cavity, of a metal flow system which includes a die or mould tool means which defines at least one runner from which molten magnesium alloy is able to be injected into the die cavity. The metal flow system is of a form providing for control of metal flow velocities within the flow system, whereby substantially all of the metal flowing throughout the die cavity is in a viscous or semi-solid state. Filling of the die cavity is able to proceed progressively by semi-solid fronts of metal moving away from a gate or other site of injection. The flow of magnesium alloy from the runner may be via at least one controlled expansion region of the metal flow system in which region the metal flow is able to spread laterally, with respect to its direction of injection, with a resultant reduction in its flow velocity relative to its velocity in the runner.

